

- 8 -

In the Abstract:

Please amend the abstract as follows:

Abstract

A III nitride buffer film including at least Al element and having a screw-type
| dislocation density of $1 \times 10^8/\text{cm}^2$ or belowless is formed on a base ~~made off~~from a sapphire
single crystal, etc., to fabricate an epitaxial base substrate. Then, a III nitride underfilm is
formed on the III nitride buffer film, to fabricate an epitaxial substrate.